

Design: **ÁRABE**



BASIC INFORMATION

Tariff item number	5801370000	Number of colour ways	3
Country of origin	India	MID	INDDEHOM16
Vertical repeat cm	46.00	Characteristics	Velvet
Horizontal repeat cm	36.50	Vertical repeat inch	18.11
Face in	Yes	Horizontal repeat inch	14.37
Full roll diameter inch	10.63	Full roll diameter cm	27
Minimum for special colour m	1000	Average piece length m	30
		Delivery time weeks special lab dip	4

CARE AND USAGE

Care code comments iron on reverse side

Care codes

Care code for washing °C Do not wash Care code for bleaching Do not bleach



Use codes

Curtains
Upholstery ✓
Accessories ✓

Curtains and draperies
Bed covering ✓
Maritime

Design: **ÁRABE**

FABRIC SPECIFICATIONS

Composition	41% Polyester, 41% Viscose, 18% Cotton	Average yarn number	14.23
Construction	31.89x18.89	Woven	Yes
Useable width cm	1.46	Useable width inch	57.48
Full width cm	148	Full width inch	58.27
Weight g/m ²	503	Thickness mm	0.000
Colouring type	Yarn dyed	Filament or staple	77% staple + 23% filament
Textured or non textured	77% not textured + 23% textured		

Treatment

Bio treatment	Flame retardant
Soil and stain repellent	Brushed/emersised
Backing	Anti-bacterial/microbial
Mildew resistant	Odour resistant
Stain-free technology	PFC free
Other treatment	No treatment ✓

Type of finish

Calender	Sanforized
Thermofixed	Washed
Airo ✓	Stenter

Type of print or dye

Disperse ✓	Reactive ✓
Vat	Pigment

Weaving type

Plain	Twill
Satin	Dobby
Jacquard ✓	Pile
Other	

Design: **ÁRABE**

FABRIC TYPE

There are no technical details for this section.

ENVIRONMENTAL STANDARDS



Prop 65

Yes

FR STANDARDS

BS5852 source 0
FMVSS 302 Pass

Yes
Yes

CAL 117 Complies
NFPA 260

Yes
Yes

Design: **ÁRABE**

MECHANICAL PERFORMANCE

Martindale rubs	90,000	Colour fastness to light	6
Wyzenbeek double rubs	100,000	Pilling	4
Brush pilling	4	Wyzenbeek wire screen double rubs - residential use, stopped after 15 000 double rubs	15,000
Wyzenbeek cotton duck type heavy upholstery	Yes	Wyzenbeek wire screen heavy duty	Yes
Colour fastness to light - ISO 105-B02			
Colour fastness to light	6		
Colour fastness to water - ISO 105-E01			
Colour fastness to water	4-5		
Colour fastness to dry rub - ISO 105-X12			
Colour fastness dry rub	4-5		
Colour fastness to wet rub - ISO 105-X12			
Colour fastness wet rub	4-5		
Colour fastness to wear - ISO 12947-2			
Colour fastness to wear	4		
Tearing strength - ISO 13937-3			
Tearing strength warp N	85	Tearing strength weft N	120
Tensile strength - ISO 13934-1			
Tensile strength warp N/5cm	2000	Tensile strength weft N/5cm	1600
Elongation - ISO 13934-1			
Elongation warp %	35	Elongation weft %	19.5
Seam slippage - ISO 13936-2			
Seam slippage warp mm	2	Seam slippage weft mm	2
Dimensional stability (indicated in %) - ISO 3759			
Dimensional change warp	-0.19	Dimensional change warp after ironing with steam	-0.40
Dimensional change warp after ironing without steam	0.07	Dimensional change weft	-0.23
Dimensional change weft after ironing with steam	0.07	Dimensional change weft after ironing without steam	0.13

Design: **ÁRABE**

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-2.45	Dimensional change warp after ironing	-2.31
Dimensional change weft	-1.69	Dimensional change weft after ironing	-1.59
Colour fastness ISO 105 C06	4		

Resistance to domestic washing 60° C, indicated in % - ISO 6330

Dimensional change warp	-3.81	Dimensional change warp after ironing	-3.84
Dimensional change weft	-2.28	Dimensional change weft after ironing	-1.98
Colour fastness ISO 105 C06	4-5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.69	Dimensional change warp after ironing	-0.79
Dimensional change weft	-1.26	Dimensional change weft after ironing	-0.79
Colour fastness ISO 105 D01	4-5		

Design: **ÁRABE**

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	300D/96	Warp Textured	Yes
Warp Threads per cm	31.89	Warp TPM	0

Yarn 2

Weft Composition	48% Polyester, 52% Cotton	Weft Is Not High Tenacity	Yes
Weft Sizes	2/16	Weft Threads per cm	18.89
Weft TPM	0		

Yarn 3

Pile Composition	100% Viscose	Pile Is Not High Tenacity	Yes
Pile Is Staple	Yes	Pile Sizes	2/24s
Pile Threads per cm	10.39	Pile TPM	0

Yarn 4

Pile Composition	100% Viscose	Pile Is Not High Tenacity	Yes
Pile Is Staple	Yes	Pile Sizes	2/24s
Pile Threads per cm	10.39	Pile TPM	0

DOWNLOADS / CERTIFICATES

There are no technical details for this section.