

Design: Balada



BASIC INFORMATION

Number of colour ways	3	Tariff item number	5515129000
MID	INDDEEXP16	Country of origin	India
Characteristics	Jacquard	Vertical repeat cm	25.50
Vertical repeat inch	10.04	Horizontal repeat cm	21.20
Horizontal repeat inch	8.35	Double folded face in	Yes
Full roll diameter cm	0	Full roll diameter inch	0
Average piece length m	40	Minimum for special colour m	1000
Delivery time weeks special lab dip	4	Railroaded	Yes

CARE AND USAGE

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains ✓
Upholstery
Accessories ✓

Curtains and draperies ✓
Bed covering
Maritime

Design: Balada

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	60.08
Construction	107x41.4	Woven	Yes
Useable width cm	3.06	Useable width inch	120.47
Full width cm	308	Full width inch	121.26
Weight g/m ²	247	Thickness mm	0.601
Colouring type	Yarn dyed	Filament or staple	64% staple + 34% filament
Textured or non textured	64% not textured + 36% textured		

Treatment

Bio treatment	Flame retardant
Soil and stain repellent	Brushed/emersed
Backing	Anti-bacterial/microbial
Mildew resistant	Odour resistant
Stain-free technology	PFC free
Other treatment	No treatment ✓

Type of finish

Calender	Sanforized
Thermofixed	Washed
Airo	Stenter ✓

Type of print or dye

Disperse ✓	Reactive
Vat	Pigment

Weaving type

Plain	Twill
Satin	Dobby
Jacquard ✓	Pile
Other	

Design: Balada

FABRIC TYPE

There are no technical details for this section.

ENVIRONMENTAL STANDARDS



FR STANDARDS

BS5867 part 2 type B	No	CAL 117 Complies	Yes
CANULC-S109 Small flame test	No	FMVSS 302 Pass	Yes
NFPA 260	Yes	NFPA 701	Yes

Design: Balada

MECHANICAL PERFORMANCE

Martindale rubs	8,000	Colour fastness to light	6
Wyzenbeek double rubs	55,000	Pilling	4-5
Brush pilling	4-5	Wyzenbeek wire screen double rubs - residential use, stopped after 15 000 double rubs	15,000
Wyzenbeek cotton duck type heavy upholstery	Yes	Wyzenbeek wire screen heavy duty	Yes
Colour fastness to light - ISO 105-B02			
Colour fastness to light	6		
Colour fastness to water - ISO 105-E01			
Colour fastness to water	5		
Colour fastness to dry rub - ISO 105-X12			
Colour fastness dry rub	4-5		
Colour fastness to wet rub - ISO 105-X12			
Colour fastness wet rub	4-5		
Colour fastness to wear - ISO 12947-2			
Colour fastness to wear	4-5		
Tearing strength - ISO 13937-3			
Tearing strength warp N	110	Tearing strength weft N	49
Tensile strength - ISO 13934-1			
Tensile strength warp N/5cm	1300	Tensile strength weft N/5cm	1800
Elongation - ISO 13934-1			
Elongation warp %	40.5	Elongation weft %	29.5
Seam slippage - ISO 13936-2			
Seam slippage warp mm	3	Seam slippage weft mm	4
Dimensional stability (indicated in %) - ISO 3759			
Dimensional change warp	0.00	Dimensional change warp after ironing with steam	0.00
Dimensional change warp after ironing without steam	0.13	Dimensional change weft	0.00
Dimensional change weft after ironing with steam	0.20	Dimensional change weft after ironing without steam	0.07

Design: Balada

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.59	Dimensional change warp after ironing	-0.46
Dimensional change weft	-0.13	Dimensional change weft after ironing	-0.07
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-1.62	Dimensional change warp after ironing	-1.52
Dimensional change weft	-0.30	Dimensional change weft after ironing	-0.20
Colour fastness ISO 105 C06	4-5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.49	Dimensional change warp after ironing	-0.33
Dimensional change weft	-0.30	Dimensional change weft after ironing	-0.33
Colour fastness ISO 105 D01	5		

Design: Balada

CONSTRUCTION

Yarn 1

Weft Composition	100% Polyester	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	2/30's Ne
Weft Threads per cm	13.8	Weft TPM	590

Yarn 2

Weft Composition	100% Polyester	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	2/43's Ne
Weft Threads per cm	13.8	Weft TPM	580

Yarn 3

Weft Composition	100% Polyester	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	150D
Weft Threads per cm	13.8	Weft TPM	250

Yarn 4

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	65D	Warp Textured	Yes
Warp Threads per cm	107	Warp TPM	450

DOWNLOADS / CERTIFICATES

There are no technical details for this section.