

Design: GARAJAU



BASIC INFORMATION

Number of colour ways	30	Tariff item number	5407920000
MID	INDEEHOM16	Country of origin	India
Characteristics	Flat Weave	Vertical repeat cm	Plain
Vertical repeat inch	Plain	Horizontal repeat cm	Plain
Horizontal repeat inch	Plain	Double folded face in	Yes
Full roll diameter cm	19	Full roll diameter inch	7.48
Average piece length m	30	Minimum for special colour m	1000
Delivery time weeks special lab dip	2	Railroaded	Yes

Design: GARAJAU

CARE AND USAGE

Type of finish

soft + stenter

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains ✓
Upholstery
Accessories ✓

Curtains and draperies ✓
Bed covering ✓
Maritime

Design: GARAJAU

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	18.39
Construction	33.07x14.18	Woven	Yes
Useable width cm	3.04	Useable width inch	119.69
Full width cm	306	Full width inch	120.47
Weight g/m ²	257	Thickness mm	0.460
Colouring type	Piece dyed	Filament or staple	59% filament + 41% staple
Textured or non textured	70% not textured + 30% textured	Finish type	soft + stenter

Treatment

Bio treatment	Flame retardant <input checked="" type="checkbox"/>
Soil and stain repellent	Brushed/emerised
Backing	Anti-bacterial/microbial
Mildew resistant	Odour resistant
Stain-free technology	PFC free
Other treatment	No treatment

Type of finish

Calender	Sanforized
Thermofixed	Washed
Airo	Stenter

Type of print or dye

Disperse <input checked="" type="checkbox"/>	Reactive
Vat	Pigment

Weaving type

Plain	Twill
Satin	Dobby <input checked="" type="checkbox"/>
Jacquard	Pile
Other	

Design: GARAJAU

FABRIC TYPE

There are no technical details for this section.

ENVIRONMENTAL STANDARDS



FR STANDARDS

BS5867 part 2 type B
FMVSS 302 Pass

No
Yes

CANULC-S109 Small flame test
NFPA 701

No
Yes

Design: GARAJAU

MECHANICAL PERFORMANCE

Martindale rubs	35,000	Colour fastness to light	4-5
Wyzenbeek double rubs	20,000	Pilling	3-4
Brush pilling	4	Wyzenbeek wire screen double rubs - residential use, stopped after 15 000 double rubs	9,000
Wyzenbeek cotton duck type general upholstery	Yes	Wyzenbeek wire screen medium duty	Yes
Colour fastness to light - ISO 105-B02			
Colour fastness to light	4-5		
Colour fastness to water - ISO 105-E01			
Colour fastness to water	5		
Colour fastness to dry rub - ISO 105-X12			
Colour fastness dry rub	4-5		
Colour fastness to wet rub - ISO 105-X12			
Colour fastness wet rub	4-5		
Colour fastness to wear - ISO 12947-2			
Colour fastness to wear	3-4		
Tearing strength - ISO 13937-3			
Tearing strength warp N	140	Tearing strength weft N	48
Tensile strength - ISO 13934-1			
Tensile strength warp N/5cm	1000	Tensile strength weft N/5cm	910
Elongation - ISO 13934-1			
Elongation warp %	35	Elongation weft %	19
Seam slippage - ISO 13936-2			
Seam slippage warp mm	6	Seam slippage weft mm	6
Dimensional stability (indicated in %) - ISO 3759			
Dimensional change warp	-0.14	Dimensional change warp after ironing with steam	-0.60
Dimensional change warp after ironing without steam	0.00	Dimensional change weft	0.14
Dimensional change weft after ironing with steam	-0.13	Dimensional change weft after ironing without steam	0.07

Design: GARAJAU

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.63	Dimensional change warp after ironing	-0.73
Dimensional change weft	-0.07	Dimensional change weft after ironing	-0.13
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 60° C, indicated in % - ISO 6330

Dimensional change warp	-2.02	Dimensional change warp after ironing	-1.72
Dimensional change weft	0.03	Dimensional change weft after ironing	-0.07
Colour fastness ISO 105 C06	4-5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.85	Dimensional change warp after ironing	0.00
Dimensional change weft	-0.03	Dimensional change weft after ironing	0.00
Colour fastness ISO 105 D01	5		

Design: GARAJAU

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Sizes	200D
Warp Threads per cm	33.07	Warp TPM	0

Yarn 2

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Textured	Yes
Weft Sizes	450D	Weft Textured	Yes
Weft Threads per cm	7.09	Weft TPM	0

Yarn 3

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Is Textured	Yes	Weft Sizes	1250D
Weft Textured	Yes	Weft Threads per cm	7.09
Weft TPM	0		

DOWNLOADS / CERTIFICATES

There are no technical details for this section.