


Design: LANTERNIM



BASIC INFORMATION

Brand	Bru	Number of colour ways	3
Tariff item number	5801370000	MID	INDDEHOM16
Country of origin	India	Characteristics	Velvet
Vertical repeat cm	28.00	Vertical repeat inch	11.02
Horizontal repeat cm	73.50	Horizontal repeat inch	28.94
Face in	Yes	Full roll diameter cm	40
Full roll diameter inch	15.75	Average piece length m	35
Minimum for special colour m	1000	Delivery time weeks special lab dip	4

CARE AND USAGE

Care code comments

Iron on reverse side

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains

Upholstery ✓

Accessories ✓

Curtains and draperies

Bed covering

Maritime

Design: LANTERNIM

FABRIC SPECIFICATIONS

Composition	64% Polyester, 36% Viscose	Average yarn number	9.62
Construction	31.88x20.47	Woven	Yes
Useable width cm	1.47	Useable width inch	57.87
Full width cm	149	Full width inch	58.66
Weight g/m ²	528	Thickness mm	1.160
Colouring type	Yarn dyed	Filament or staple	100% filament
Textured or non textured	20% textured, 80% not textured		

Treatment

Bio treatment	Flame retardant
Soil and stain repellent	Brushed/emersed
Backing	Anti-bacterial/microbial
Mildew resistant	Odour resistant
Stain-free technology	PFC free
Other treatment	No treatment ✓

Type of finish

Calender	Sanforized
Thermofixed	Washed
Airo ✓	Stenter

Type of print or dye

Disperse	Reactive ✓
Vat	Pigment

Weaving type

Plain	Twill
Satin	Dobby
Jacquard ✓	Pile
Other	

Design: LANTERNIM

FABRIC TYPE

There are no technical details for this section.

ENVIRONMENTAL STANDARDS



Prop 65

Yes

FR STANDARDS

BS5852 source 0
FMVSS 302 Pass

Yes
Yes

CAL 117 Complies
NFPA 260

Yes
Yes

Design: LANTERNIM

MECHANICAL PERFORMANCE

Martindale rubs	20,000	Wyzenbeek double rubs	20,000
Pilling	4-5	Brush pilling	4
Wyzenbeek wire screen double rubs - residential use, stopped after 15 000 double rubs	15,000	Wyzenbeek cotton duck type general upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		
Colour fastness to water - ISO 105-E01			
Colour fastness to water	5		
Colour fastness to dry rub - ISO 105-X12			
Colour fastness dry rub	4-5		
Colour fastness to wet rub - ISO 105-X12			
Colour fastness wet rub	4-5		
Tearing strength - ISO 13937-3			
Tearing strength warp N	230	Tearing strength weft N	100
Tensile strength - ISO 13934-1			
Tensile strength warp N/5cm	950	Tensile strength weft N/5cm	2000
Elongation - ISO 13934-1			
Elongation warp %	45.5	Elongation weft %	15
Seam slippage - ISO 13936-2			
Seam slippage warp mm	3	Seam slippage weft mm	4
Dimensional stability (indicated in %) - ISO 3759			
Dimensional change warp	0.07	Dimensional change warp after ironing with steam	0.00
Dimensional change warp after ironing without steam	0.13	Dimensional change weft	0.08
Dimensional change weft after ironing with steam	0.07	Dimensional change weft after ironing without steam	0.13

Design: LANTERNIM

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-1.16	Dimensional change warp after ironing	-0.99
Dimensional change weft	0.07	Dimensional change weft after ironing	-0.07
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-2.05	Dimensional change warp after ironing	-1.99
Dimensional change weft	-0.33	Dimensional change weft after ironing	-0.46
Colour fastness ISO 105 C06	4-5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.03	Dimensional change warp after ironing	0.00
Dimensional change weft	-0.07	Dimensional change weft after ironing	0.00
Colour fastness ISO 105 D01	5		

Design: LANTERNIM

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	300/450	Warp Textured	Yes
Warp Threads per cm	31.88	Warp TPM	0

Yarn 2

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Sizes	950D
Weft Threads per cm	18.9	Weft TPM	0

Yarn 3

Weft Composition	100% Viscose	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	2/24s
Weft Threads per cm	0	Weft TPM	0

DOWNLOADS / CERTIFICATES

There are no technical details for this section.