

Design: Marty

BASIC INFORMATION

Brand	Bru	Number of colour ways	4
Tariff item number	5209510099	MID	ESTEXST108
Country of origin	Spain	Characteristics	Print
Vertical repeat cm	31.50	Vertical repeat inch	12.40
Horizontal repeat cm	68.00	Horizontal repeat inch	26.77
Face in	Yes	Full roll diameter cm	18
Full roll diameter inch	7.09	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE AND USAGE

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains ✓
 Upholstery ✓
 Accessories ✓

Curtains and draperies ✓
 Bed covering ✓
 Maritime

ENVIRONMENTAL STANDARDS



FR STANDARDS

BS5852 source 0	Yes	CAL 117 Complies	No
FMVSS 302 Pass	No	NFPA 260	Yes

Design: Marty

FABRIC SPECIFICATIONS

Composition	100% Cotton	Average yarn number	14.29
Construction	28x12	Woven	Yes
Useable width cm	1.38	Useable width inch	54.33
Full width cm	140	Full width inch	55.12
Weight g/m ²	280	Thickness mm	0.620
Colouring type	Printed	Filament or staple	100% staple
Textured or non textured	100% not textured	Other treatment specification	softener

Treatment

Bio treatment	Flame retardant
Soil and stain repellent	Brushed/emersed
Backing	Anti-bacterial/microbial
Mildew resistant	Odour resistant
Stain-free technology	PFC free
Other treatment ✓	No treatment

Type of finish

Calender	Sanforized
Thermofixed ✓	Washed
Airo	Stenter

Type of print or dye

Disperse	Reactive
Vat	Pigment ✓

Weaving type

Plain ✓	Twill
Satin	Dobby
Jacquard	Pile
Other	

Design: Marty

MECHANICAL PERFORMANCE

Martindale rubs	18,000	Colour fastness to light	6
Wyzenbeek double rubs	90,000	Pilling	4
Brush pilling	4-5	Wyzenbeek wire screen double rubs - residential use, stopped after 15 000 double rubs	15,000
Wyzenbeek cotton duck type heavy upholstery	Yes	Wyzenbeek wire screen heavy duty	Yes
Colour fastness to light - ISO 105-B02			
Colour fastness to light	6		
Colour fastness to water - ISO 105-E01			
Colour fastness to water	4-5		
Colour fastness to dry rub - ISO 105-X12			
Colour fastness dry rub	4-5		
Colour fastness to wet rub - ISO 105-X12			
Colour fastness wet rub	3		
Colour fastness to wear - ISO 12947-2			
Colour fastness to wear	3-4		
Tearing strength - ISO 13937-3			
Tearing strength warp N	15	Tearing strength weft N	26
Tensile strength - ISO 13934-1			
Tensile strength warp N/5cm	630	Tensile strength weft N/5cm	440
Elongation - ISO 13934-1			
Elongation warp %	18.50	Elongation weft %	11.50
Seam slippage - ISO 13936-2			
Seam slippage warp mm	5	Seam slippage weft mm	5
Dimensional stability (indicated in %) - ISO 3759			
Dimensional change warp	0.10	Dimensional change warp after ironing with steam	0.20
Dimensional change warp after ironing without steam	0.07	Dimensional change weft	-0.07
Dimensional change weft after ironing with steam	-0.13	Dimensional change weft after ironing without steam	0.00

Design: Marty

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-3.00	Dimensional change warp after ironing	-3.00
Dimensional change weft	-1.93	Dimensional change weft after ironing	-1.79
Colour fastness ISO 105 C06	4		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-6.37	Dimensional change warp after ironing	-6.04
Dimensional change weft	-2.36	Dimensional change weft after ironing	-1.99
Colour fastness ISO 105 C06	4		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.09	Dimensional change warp after ironing	0.00
Dimensional change weft	-0.17	Dimensional change weft after ironing	0.00
Colour fastness ISO 105 D01	4-5		

CONSTRUCTION

Yarn 1

Warp Composition	100% Cotton	Warp Is Not High Tenacity	Yes
Warp Is Staple	Yes	Warp Sizes	10 1/C NE
Warp Threads per cm	28	Warp TPM	0

Yarn 2

Weft Composition	100% Cotton	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	7 1/C NE
Weft Threads per cm	12	Weft TPM	0