

DESIGN: ODALYS

BASIC INFORMATION

Number of colour ways	4	Tariff item number	5309290000
MID	INDEEXP16	Country of origin	India
Characteristics	Sheer	Vertical repeat cm	Stripe
Vertical repeat inch	Stripe	Horizontal repeat cm	2.30
Horizontal repeat inch	0.91	Double folded face in	Yes
Full roll diameter cm	25	Full roll diameter inch	9.84
Average piece length m	50	Minimum for special colour m	1000
Delivery time weeks special lab dip	4	Railroaded	Yes

CARE AND USAGE

Care codes



Care code for bleaching Do not bleach

Use codes

Curtains Yes Curtains and draperies Yes

ENVIRONMENTAL STANDARDS



GRS post-consumer



STANDARD 100
2111232
Centexbel



Certified by Control Union
CU1036513

Yes



Prop 65

Yes

FR STANDARDS

FMVSS 302 Pass No

DESIGN: ODALYS

FABRIC SPECIFICATIONS

Composition	40% Recycled Polyester, 38% Linen, 22% Organic Cotton	Average yarn number	22.48
Construction	16.5x12.5	Woven	Yes
Useable width cm	3.02	Useable width inch	118.9
Full width cm	304	Full width inch	119.69
Weight g/m ²	129	Thickness mm	0.420
Colouring type	Yarn dyed	Filament or staple	98% staple + 2% filament
Textured or non textured	98% not textured + 2% textured		

Treatment

No treatment Yes

Type of finish

Stenter Yes

Type of print or dye

Disperse Yes Reactive Yes

Weaving type

Dobby Yes

FABRIC TYPE

There are no technical details for this section.

DESIGN: ODALYS

MECHANICAL PERFORMANCE

Colour fastness to light	6		
Colour fastness to light - ISO 105-B02			
Colour fastness to light	6		
Colour fastness to water - ISO 105-E01			
Colour fastness to water	5		
Tearing strength - ISO 13937-3			
Tearing strength warp N	39	Tearing strength weft N	80
Tensile strength - ISO 13934-1			
Tensile strength warp N/5cm	510	Tensile strength weft N/5cm	350
Elongation - ISO 13934-1			
Elongation warp %	26.5	Elongation weft %	4.6
Dimensional stability (indicated in %) - ISO 3759			
Dimensional change warp	0.00	Dimensional change warp after ironing with steam	-0.07
Dimensional change warp after ironing without steam	0.13	Dimensional change weft	0.00
Dimensional change weft after ironing with steam	0.13	Dimensional change weft after ironing without steam	0.07

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.36	Dimensional change warp after ironing	-0.40
Dimensional change weft	-2.29	Dimensional change weft after ironing	-1.99
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-1.23	Dimensional change warp after ironing	-0.86
Dimensional change weft	-3.88	Dimensional change weft after ironing	-3.92
Colour fastness ISO 105 C06	4-5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.96	Dimensional change warp after ironing	-0.33
Dimensional change weft	-0.50	Dimensional change weft after ironing	-0.33
Colour fastness ISO 105 D01	4-5		

DESIGN: ODALYS

CONSTRUCTION

Yarn 1

Warp Composition	66% Recycled Polyester, 34% Organic Cotton	Warp Is Not High Tenacity	Yes
Warp Is Staple	Yes	Warp Sizes	2/36's
Warp Threads per cm	16.5	Warp TPM	460

Yarn 2

Weft Composition	54% Organic Cotton, 44% Recycled Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Is Textured	Yes	Weft Sizes	2.8 NM
Weft Textured	Yes	Weft Threads per cm	0.4
Weft TPM	400		

Yarn 3

Weft Composition	100% Linen	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	44 lea linen
Weft Threads per cm	12.1	Weft TPM	400

DOWNLOADS / CERTIFICATES

There are no technical details for this section.