

Design: OLIVAL



BASIC INFORMATION

Brand	Bru	Number of colour ways	5
Tariff item number	5801360000	MID	INDDEHOM16
Country of origin	India	Characteristics	Chenille
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	29.2
Full roll diameter inch	11.5	Average piece length m	40
Minimum for special colour m	1000	Delivery time weeks special lab dip	4

CARE AND USAGE

Care code comments iron on reverse side

Care codes

Care code for washing °C Do not wash Care code for bleaching Do not bleach



Use codes

- | | |
|---------------|--------------------------|
| Curtains ✓ | Curtains and draperies ✓ |
| Upholstery ✓ | Bed covering ✓ |
| Accessories ✓ | Maritime |

Design: OLIVAL

FABRIC SPECIFICATIONS

Composition	48% Viscose, 35% Polyester, 17% Cotton	Average yarn number	7.78
Construction	32.89x13.38	Woven	Yes
Useable width cm	1.38	Useable width inch	54.33
Full width cm	140	Full width inch	55.12
Weight g/m ²	595	Thickness mm	0.000
Colouring type	Yarn dyed	Filament or staple	75% staple + 25% filament
Textured or non textured	75% not textured + 25% textured		

Treatment

Bio treatment	Flame retardant
Soil and stain repellent	Brushed/emersised
Backing	Anti-bacterial/microbial
Mildew resistant	Odour resistant
Stain-free technology	PFC free
Other treatment	No treatment ✓

Type of finish

Calender	Sanforized
Thermofixed	Washed
Airo ✓	Stenter

Type of print or dye

Disperse ✓	Reactive ✓
Vat	Pigment

Weaving type

Plain	Twill
Satin	Dobby ✓
Jacquard	Pile
Other	

Design: OLIVAL

FABRIC TYPE

There are no technical details for this section.

ENVIRONMENTAL STANDARDS



FR STANDARDS

BS5852 source 0
FMVSS 302 Pass

Yes
Yes

CAL 117 Complies
NFPA 260

Yes
Yes

Design: OLIVAL

MECHANICAL PERFORMANCE

Martindale rubs	90,000	Colour fastness to light	6
Wyzenbeek double rubs	200,000	Pilling	4
Brush pilling	4-5	Wyzenbeek wire screen double rubs - residential use, stopped after 15 000 double rubs	15,000
Wyzenbeek cotton duck type heavy upholstery	Yes	Wyzenbeek wire screen heavy duty	Yes
Colour fastness to light - ISO 105-B02			
Colour fastness to light	6		
Colour fastness to water - ISO 105-E01			
Colour fastness to water	5		
Colour fastness to dry rub - ISO 105-X12			
Colour fastness dry rub	4-5		
Colour fastness to wet rub - ISO 105-X12			
Colour fastness wet rub	4		
Colour fastness to wear - ISO 12947-2			
Colour fastness to wear	4		
Tearing strength - ISO 13937-3			
Tearing strength warp N	160	Tearing strength weft N	170
Tensile strength - ISO 13934-1			
Tensile strength warp N/5cm	1800	Tensile strength weft N/5cm	760
Elongation - ISO 13934-1			
Elongation warp %	40.5	Elongation weft %	29.5
Seam slippage - ISO 13936-2			
Seam slippage warp mm	6	Seam slippage weft mm	4
Dimensional stability (indicated in %) - ISO 3759			
Dimensional change warp	-0.21	Dimensional change warp after ironing with steam	0.00
Dimensional change warp after ironing without steam	0.07	Dimensional change weft	0.00
Dimensional change weft after ironing with steam	0.27	Dimensional change weft after ironing without steam	0.20

Design: OLIVAL

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-3.94	Dimensional change warp after ironing	-3.58
Dimensional change weft	-4.11	Dimensional change weft after ironing	-3.25
Colour fastness ISO 105 C06	4		

Resistance to domestic washing 60° C, indicated in % - ISO 6330

Dimensional change warp	-12.77	Dimensional change warp after ironing	-11.29
Dimensional change weft	-14.21	Dimensional change weft after ironing	-12.64
Colour fastness ISO 105 C06	4-5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.46	Dimensional change warp after ironing	0.26
Dimensional change weft	-0.07	Dimensional change weft after ironing	0.26
Colour fastness ISO 105 D01	5		

Design: OLIVAL

CONSTRUCTION

Yarn 1

Warp Composition	74% Viscose, 26% Cotton	Warp Is Not High Tenacity	Yes
Warp Is Staple	Yes	Warp Sizes	3 NM
Warp Threads per cm	4.13	Warp TPM	NA

Yarn 2

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	300D	Warp Textured	Yes
Warp Threads per cm	28.76	Warp TPM	NA

Yarn 3

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Textured	Yes
Weft Sizes	300D	Weft Textured	Yes
Weft Threads per cm	6.69	Weft TPM	NA

Yarn 4

Weft Composition	60% Polyester, 40% Viscose	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	3.5NM
Weft Threads per cm	3.35	Weft TPM	NA

Yarn 5

Weft Composition	74% Viscose, 26% Cotton	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	3NM
Weft Threads per cm	1.67	Weft TPM	NA

Yarn 6

Weft Composition	74% Viscose, 26% Cotton	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	3NM
Weft Threads per cm	1.67	Weft TPM	NA

Design: OLIVAL

DOWNLOADS / CERTIFICATES

There are no technical details for this section.