

Design: PAUL

BASIC INFORMATION

Brand	Bru	Number of colour ways	42
Tariff item number	5801370000	MID	INDDEHOM16
Country of origin	India	Characteristics	Velvet
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	35
Full roll diameter inch	13.78	Average piece length m	30
Minimum for special colour m	1000	Delivery time weeks special lab dip	2
Suspended box	Yes		

CARE AND USAGE

Care codes

Care code for washing °C	Do not wash	Care code for bleaching	Do not bleach
			

Use codes

Curtains ✓	Curtains and draperies ✓
Upholstery ✓	Bed covering ✓
Accessories ✓	Maritime

ENVIRONMENTAL STANDARDS



FR STANDARDS

BS5852 source 0	Yes	CAL 117 Complies	No
FMVSS 302 Pass	Yes	NFPA 260	No

COLLECTION: MONT BLANC

DESIGN: MONT BLANC

FABRIC SPECIFICATIONS

Composition	56% Viscose, 44% Cotton	Average yarn number	6.58
Construction	23x26	Woven	Yes
Useable width cm	1.47	Useable width inch	57.87
Full width cm	149	Full width inch	58.66
Weight g/m ²	580	Thickness mm	0.000
Colouring type	Piece dyed	Filament or staple	100% Staple

Treatment

Bio treatment	Flame retardant
Soil and stain repellent	Brushed/emersised
Backing	Anti-bacterial/microbial
Mildew resistant	Odour resistant
Stain-free technology	PFC free
Other treatment	No treatment ✓

Type of finish

Calender	Sanforized
Thermofixed	Washed
Airo	Stenter ✓

Type of print or dye

Disperse	Reactive ✓
Vat	Pigment

Weaving type

Plain	Twill
Satin	Dobby ✓
Jacquard	Pile
Other	

FABRIC TYPE

There are no technical details for this section.

COLLECTION: MONT BLANC

DESIGN: MONT BLANC

MECHANICAL PERFORMANCE

Martindale rubs	100,000	Colour fastness to light	6
Wyzenbeek double rubs	200,000	Pilling	4-5
Wyzenbeek wire screen double rubs - residential use, stopped after 15 000 double rubs	15,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen heavy duty	Yes		
Colour fastness to light - ISO 105-B02			
Colour fastness to light	6		
Colour fastness to water - ISO 105-E01			
Colour fastness to water	4		
Colour fastness to dry rub - ISO 105-X12			
Colour fastness dry rub	4-5		
Colour fastness to wet rub - ISO 105-X12			
Colour fastness wet rub	3-4		
Colour fastness to wear - ISO 12947-2			
Colour fastness to wear	4-5		
Tearing strength - ISO 13937-3			
Tearing strength warp N	29	Tearing strength weft N	29
Tensile strength - ISO 13934-1			
Tensile strength warp N/5cm	600	Tensile strength weft N/5cm	950
Elongation - ISO 13934-1			
Elongation warp %	12.5	Elongation weft %	14.5
Seam slippage - ISO 13936-2			
Seam slippage warp mm	3.0	Seam slippage weft mm	3.0
Dimensional stability (indicated in %) - ISO 3759			
Dimensional change warp	-0.17	Dimensional change warp after ironing with steam	0.00
Dimensional change warp after ironing without steam	0.00	Dimensional change weft	0.00
Dimensional change weft after ironing with steam	0.13	Dimensional change weft after ironing without steam	0.07

COLLECTION: MONT BLANC

DESIGN: MONT BLANC

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-2.50	Dimensional change warp after ironing	-2.33
Dimensional change weft	0.33	Dimensional change weft after ironing	0.67
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-3.38	Dimensional change warp after ironing	-3.05
Dimensional change weft	0.07	Dimensional change weft after ironing	0.07
Colour fastness ISO 105 C06	3-4		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.14	Dimensional change warp after ironing	-0.26
Dimensional change weft	-0.40	Dimensional change weft after ironing	-0.26
Colour fastness ISO 105 D01	5		

[See fabric on Twinbru](#)

COLLECTION: MONT BLANC

DESIGN: MONT BLANC

CONSTRUCTION

Yarn 1

Warp Composition	100% Cotton	Warp Is Not High Tenacity	Yes
Warp Is Staple	Yes	Warp Sizes	2/30 combed RS WVG Cotton
Warp Threads per cm	11.02	Warp TPM	0

Yarn 2

Pile Composition	100% Viscose	Pile Is Not High Tenacity	Yes
Pile Is Staple	Yes	Pile Sizes	2/24s viscose grey
Pile Threads per cm	0	Pile TPM	0

Yarn 3

Warp Composition	100% Cotton	Warp Is Not High Tenacity	Yes
Warp Is Staple	Yes	Warp Sizes	2/20 combed RS WVG Cotton
Warp Threads per cm	11.02	Warp TPM	0

Yarn 4

Weft Composition	100% Cotton	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	2/16 carded RS WVG slub cotton
Weft Threads per cm	16.11	Weft TPM	0

DOWNLOADS / CERTIFICATES

There are no technical details for this section.