

Design: SALIR

**BASIC INFORMATION**

Brand	Fabric Library	Number of colour ways	20
Tariff item number	5407613000	MID	CNHANEAS18
Country of origin	China	Characteristics	Texture
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	26
Full roll diameter inch	10.24	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

**CARE AND USAGE**

Care codes



Care code for bleaching

Do not bleach

Use codes

- Curtains
- Upholstery ✓
- Accessories ✓

- Curtains and draperies
- Bed covering ✓
- Maritime

Design: SALIR

**FABRIC SPECIFICATIONS**

Composition	100% Polyester	Average yarn number	8.56
Construction	17x14	Woven	Yes
Useable width cm	1.43	Useable width inch	56.3
Full width cm	145	Full width inch	57.09
Weight g/m <sup>2</sup>	362	Thickness mm	0.000
Colouring type	Piece dyed	Water repellent	Yes
Filament or staple	100% filament	Textured or non textured	100% not textured

**Treatment**

---

Bio treatment	Flame retardant
Soil and stain repellent	Brushed/emersed
Backing	Anti-bacterial/microbial
Mildew resistant	Odour resistant
Stain-free technology	PFC free
Other treatment	No treatment

**Type of finish**

---

Calender	Sanforized
Thermofixed	Washed
Airo	Stenter

**Type of print or dye**

---

Disperse ✓	Reactive
Vat	Pigment

**Weaving type**

---

Plain	Twill
Satin	Dobby ✓
Jacquard	Pile
Other	

Design: SALIR

### FABRIC TYPE

There are no technical details for this section.

### ENVIRONMENTAL STANDARDS



### FR STANDARDS

BS5852 source 0  
FMVSS 302 Pass

Yes  
Yes

CAL 117 Complies  
NFPA 260

Yes  
Yes

Design: SALIR

**MECHANICAL PERFORMANCE**

Martindale rubs	50,000	Colour fastness to light	5
Wyzenbeek double rubs	100,000	Pilling	4-5
Brush pilling	4-5	Wyzenbeek wire screen double rubs - residential use, stopped after 15 000 double rubs	15,000
Wyzenbeek cotton duck type heavy upholstery	Yes	Water repellent	Yes
Wyzenbeek wire screen heavy duty	Yes		

**Colour fastness to light - ISO 105-B02**

Colour fastness to light	5
--------------------------	---

**Colour fastness to water - ISO 105-E01**

Colour fastness to water	5
--------------------------	---

**Colour fastness to dry rub - ISO 105-X12**

Colour fastness dry rub	4-5
-------------------------	-----

**Colour fastness to wet rub - ISO 105-X12**

Colour fastness wet rub	4-5
-------------------------	-----

**Colour fastness to wear - ISO 12947-2**

Colour fastness to wear	4
-------------------------	---

**Tearing strength - ISO 13937-3**

Tearing strength warp N	160	Tearing strength weft N	140
-------------------------	-----	-------------------------	-----

**Tensile strength - ISO 13934-1**

Tensile strength warp N/5cm	1200	Tensile strength weft N/5cm	1500
-----------------------------	------	-----------------------------	------

**Elongation - ISO 13934-1**

Elongation warp %	50.5	Elongation weft %	31.5
-------------------	------	-------------------	------

**Seam slippage - ISO 13936-2**

Seam slippage warp mm	4	Seam slippage weft mm	4
-----------------------	---	-----------------------	---

**Dimensional stability (indicated in %) - ISO 3759**

Dimensional change warp	-0.17	Dimensional change warp after ironing with steam	0.00
Dimensional change warp after ironing without steam	0.07	Dimensional change weft	0.14
Dimensional change weft after ironing with steam	0.07	Dimensional change weft after ironing without steam	0.13

Design: SALIR

**WASHABILITY**

**Resistance to domestic washing 30° C, indicated in % - ISO 6330**

Dimensional change warp	-1.16	Dimensional change warp after ironing	-1.06
Dimensional change weft	-0.03	Dimensional change weft after ironing	0.00
Colour fastness ISO 105 C06	4-5		

**Resistance to domestic washing 60° C, indicated in % - ISO 6330**

Dimensional change warp	-3.81	Dimensional change warp after ironing	-3.58
Dimensional change weft	-0.23	Dimensional change weft after ironing	-0.13
Colour fastness ISO 105 C06	4-5		

**Resistance to dry cleaning P, indicated in % - ISO 105 D01**

Dimensional change warp	-2.92	Dimensional change warp after ironing	0.00
Dimensional change weft	-0.23	Dimensional change weft after ironing	0.00
Colour fastness ISO 105 D01	5		

Design: SALIR

**CONSTRUCTION**

**Yarn 1**

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Sizes	300 den
Weft Threads per cm	14	Weft TPM	NA

**Yarn 2**

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Sizes	300 den
Warp Threads per cm	8	Warp TPM	NA

**Yarn 3**

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Sizes	150 den
Warp Threads per cm	9	Warp TPM	NA

**DOWNLOADS / CERTIFICATES**

There are no technical details for this section.