


TECHNICAL FABRIC DETAILS

SYROS



Syros is a fabric full of energy and dynamism, with a small geometric pattern and lots of color.



Article specification

Width	160 cm
Horizontal repeat cm	2 cm
Vertical repeat cm	2 cm
Composition	100% SOLUTION DYED ACRYLIC
Weight	420 gr/m ²
Thickness (mm)	

Cleaning Instructions



Use Code

Upholstery
Accessories
Curtains
Outdoor / Indoor
Nautic
Contract

Environmental Standards

FR Standards

Qualities



WATER RESISTANT
HIDRÓFUGO



STAIN RESISTANT
ANTIMANCHAS



MOULD RESISTANT
ANTIMOHO



DIMENSIONAL STABILITY
ESTABILIDAD DIMENSIONAL



SOFT
SUAVE



PET FRIENDLY
APTO PARA ANIMALES



UV PROTECT
PROTECCIÓN UV



UV RESISTANT
RESISTENCIA UV



DURABLE
DURADERO



KID PROOF
A PRUEBA DE NIÑOS



BREATHABLE
TRANSPIRABLE




NO CONDUCTOR
NO CONDUCTOR



EASY TO CLEAN
FÁCIL DE LIMPIAR



DISINFECTABLE
DESINFECTABLE



BLEACH
friendly

Finish

Water repellent

Anti-stain treatment

Optional Fabric Treatment

Waterproof/ Impermeable (Water Column: 1000 mm): Minimum one piece

Extra Softness + Martindale (Higher Resistance): Minimum one piece

Warranty: 5 Years

The Agora warranty covers the fabric becoming unserviceable as a result of loss of colour or strength from normal exposure conditions, including sunlight, mildew, rot and atmospheric chemicals, when properly installed, used and maintained. The warranty does not cover labour and installation costs supplied by the dealer. The warranty neither applies against deterioration of any kind due to abusive use, accidental burns, negligence or perforations.

Waterproof and flame retardant treatments: Recommended for cushions and upholstery only. Always use the lamination face inside. Do not expose the coated side to sun or light.

Mechanical Performance

Abrasion Test / Martindale Rubs (EN ISO 12947-1,2)	25.000
Piling Test (EN ISO 12945-2)	3 - 4/5
Colour Fastness to light (ISO 105-B02-2)	7/8
Colour fastness to dry rub (EN ISO 105-X12)	4-5 / 5
Tearing strength (ISO 13934-1)	Warp: 200 N Weft: 160 N
Tensile Strenght (EN ISO 13934-1)	Warp: 1900 N Weft: 2100 N
Colour fastness to artificial weathering (ISO 105-B04)	4/5
Seam slippage (ISO 13936-2)	Warp: 5.0 mm Weft: 3.0 mm
Colour fastness to chlorinated water (ISO 105-E03)	5/5
Ultraviolet protection factor UPF (AZ/NZS 4399/1996)	50+
Spray test (ISO 24920)	4/5
Shrinkage to washing (ISO 5077:2007)	Warp: -1.5% Weft: 0%
Water column mm (ISO 20811)	70



Damaceno & Antunes
Rua da Alegria 387,
4475-310 Milheirós - Maia
+351229059160 info@damaceno-antunes.pt