

Design: TATO



BASIC INFORMATION

Brand	Bru	Number of colour ways	44
Tariff item number	6001920000	MID	CNHANEAS18
Country of origin	China	Characteristics	Velvet
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	27
Full roll diameter inch	10.63	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	2
Suspended box	Yes		

Design: TATO

CARE AND USAGE

Care code comments

iron reverse side

Care codes



Care code for bleaching

Do not bleach

Use codes

- Curtains ✓
- Upholstery ✓
- Accessories ✓

- Curtains and draperies ✓
- Bed covering ✓
- Maritime

Design: TATO

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	12.99
Composition fabric	100% Polyester	Composition backing	100% Polyester
Construction	knitted	Useable width cm	1.45
Useable width inch	57.09	Full width cm	147
Full width inch	57.87	Weight g/m ²	308
Thickness mm	0.890	Colouring type	Piece dyed
Filament or staple	100% filament	Textured or non textured	100% not textured

Treatment

Bio treatment	Flame retardant
Soil and stain repellent	Brushed/emersised ✓
Backing	Anti-bacterial/microbial
Mildew resistant	Odour resistant
Stain-free technology	PFC free
Other treatment	No treatment

Type of finish

Calender	Sanforized
Thermofixed	Washed
Airo	Stenter

Type of print or dye

Disperse ✓	Reactive
Vat	Pigment

Weaving type

Plain	Twill ✓
Satin	Dobby
Jacquard	Pile
Other	

Design: TATO

FABRIC TYPE

There are no technical details for this section.

ENVIRONMENTAL STANDARDS



FR STANDARDS

BS5852 source 0
FMVSS 302 Pass

Yes
Yes

CAL 117 Complies
NFPA 260

Yes
Yes

Design: TATO

MECHANICAL PERFORMANCE

Martindale rubs	100,000	Colour fastness to light	4
Wyzenbeek double rubs	200,000	Pilling	5
Brush pilling	5	Wyzenbeek wire screen double rubs - residential use, stopped after 15 000 double rubs	15,000
Wyzenbeek cotton duck type heavy upholstery	Yes	Wyzenbeek wire screen heavy duty	Yes
Colour fastness to light - ISO 105-B02			
Colour fastness to light	4		
Colour fastness to water - ISO 105-E01			
Colour fastness to water	5		
Colour fastness to dry rub - ISO 105-X12			
Colour fastness dry rub	5		
Colour fastness to wet rub - ISO 105-X12			
Colour fastness wet rub	4-5		
Colour fastness to wear - ISO 12947-2			
Colour fastness to wear	4		
Tearing strength - ISO 13937-3			
Tearing strength warp N	90	Tearing strength weft N	58
Tensile strength - ISO 13934-1			
Tensile strength warp N/5cm	460	Tensile strength weft N/5cm	480
Elongation - ISO 13934-1			
Elongation warp %	97	Elongation weft %	21.5
Seam slippage - ISO 13936-2			
Seam slippage warp mm	3	Seam slippage weft mm	3
Dimensional stability (indicated in %) - ISO 3759			
Dimensional change warp	-0.26	Dimensional change warp after ironing with steam	-0.74
Dimensional change warp after ironing without steam	0.20	Dimensional change weft	-0.23
Dimensional change weft after ironing with steam	-0.47	Dimensional change weft after ironing without steam	0.20

Design: TATO

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-1.63	Dimensional change warp after ironing	-1.60
Dimensional change weft	-1.10	Dimensional change weft after ironing	-0.87
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-5.61	Dimensional change warp after ironing	-5.58
Dimensional change weft	-5.76	Dimensional change weft after ironing	-5.85
Colour fastness ISO 105 C06	5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-4.44	Dimensional change warp after ironing	-3.71
Dimensional change weft	-3.68	Dimensional change weft after ironing	-3.71
Colour fastness ISO 105 D01	5		

CONSTRUCTION

Yarn 1

Weft Is Not High Tenacity	Yes	Weft Threads per cm	0
---------------------------	-----	---------------------	---

Yarn 2

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Sizes	75D
Warp Threads per cm	14	Warp TPM	NA

Yarn 3

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Sizes	40D
Warp Threads per cm	26	Warp TPM	NA

Design: TATO

DOWNLOADS / CERTIFICATES

There are no technical details for this section.