

TECHNICAL SPECIFICATIONS SHEET

product information

150

quality name :	VARA		/LD DB	
			Number of colours :	<u>3</u>
composition :	<u>% 100 PES</u>		Average Rolllength :	<u>30-50</u>
weft	composition	<u>% 100 PES</u>		
	nr of threads/cm	<u>33</u>	yarn size	<u>75 DEN</u>
warp	composition	<u>% 100 PES</u>		
	nr of picks/cm	<u>30</u>	yarn size	<u>75 DEN</u>
over all width	<u>330</u>	cm	usable width	<u>330</u> cm
weight gr/m ²	<u>65</u>		dyeing methode	<u>Piece Dyed</u>
weight/rm	<u>214,5</u>		custom tariff code	

Tests

What	standard	result
martindale	ISO 14465 : 2003 + A1 : 2006	N/A
seem slippage	ISO 13936-2 : 2004	N/A
pilling	ISO 12945-2 : 2000	N/A
dim. stability		yes
light fastness	5	4-5
colour fastness dry	5	4-5
colour fastness wet	4-5	4-5
washing at 40°C extra	<2% shrinkage	Shrinkage less then 2%

care instructions

Ironing :	<u>2 dots</u>										
Mashine washable	<u>40°C</u>										
Dry cleaning :	<u>yes</u>										
Tumbling :	<u>yes</u>										
bleaching :	<u>yes</u>										
Usage :	<table border="1"> <tr> <td>Curtains</td> <td>Roman blinds</td> <td>Upholstery</td> <td>Bedding</td> <td>others :</td> </tr> <tr> <td>Yes</td> <td>Yes</td> <td></td> <td></td> <td></td> </tr> </table>	Curtains	Roman blinds	Upholstery	Bedding	others :	Yes	Yes			
Curtains	Roman blinds	Upholstery	Bedding	others :							
Yes	Yes										

additional information

MID code: on request

Composition for each fiber :

% Filament : 100% % Staple : _____

For filament Polyester fibres only :

- state by warp and weft the % textured and % non-textured fibre:

warp : % 100 CREPPE YARN weft : % 100 CREPPE YARN

- state by warp and weft the number of turnes/metre

warp : _____ weft : _____

This fabric is woven on a RAPIER WE loom.

The type of weave used in this fabric : SPECIAL CREPPE SET UP

Finishing of this product is done at : _____ °C

extra finishes / other information :

--